

# Pharmaceutical & Technical Petroleum Jellies

MOVING YOUR WORLD



## Pharmaceutical Petroleum Jellies

Product name	Colour	Kin. viscosity at 100 °C [mm <sup>2</sup> /s]	Consistency/ cone penetration 1/10mm at 25 °C	Congealing point [°C]
		DIN EN ISO 3104 ASTM D7042	DIN 51580 ASTM D937	DIN ISO 2207 ASTM D938
Pharma Petroleum Jelly CD 806	max. 1.0 Lovibond (DGF C-IV 4b)	ca. 7	ca. 160	ca. 53
SUPERLA® PJ 2000*	max. 0.5 Lovibond (DGF C-IV 4b)	ca. 13	ca. 170	ca. 50
Pharma Petroleum Jelly CD 809	min. +20 Saybolt (ASTM D156)	ca. 7	ca. 155	ca. 54
Pharma Petroleum Jelly CD 1511	max. 2.0 ASTM (ASTM D 1500)	ca. 5	ca. 160	ca. 55

\* Complies with Cosmetics Europe Recommendation No. 14.  
All our Petroleum Jellies meet the requirements of the Ph. Eur.

## Technical Petroleum Jellies

Product name	Colour	Kin. viscosity at 100 °C [mm <sup>2</sup> /s]	Consistency/ cone penetration 1/10mm at 25 °C	Congealing point [°C]
	ASTM D6045	DIN EN ISO 3104 ASTM D7042	DIN 51580	DIN ISO 2207 ASTM D938
Technical Petroleum Jelly 2046	max. 3.0	ca. 8	ca. 151	ca. 55
Technical Petroleum Jelly S-743	max. 2.5	ca. 7	ca. 190	ca. 55

The information contained in this product information is based on the experience and know-how of FUCHS LUBRICANTS GERMANY GmbH in the development and manufacturing of lubricants and represents the current state-of-the-art. The performance of our products can be influenced by a series of factors, especially the specific use, the method of application, the operational environment, component pre-treatment, possible external contamination, etc. For this reason, universally-valid statements about the function of our products are not possible. Our products must not be used in aircraft or spacecraft. Our products may be used in the manufacture of components for aircraft or spacecraft if they are removed without residue from the components prior to assembly into the aircraft or spacecraft. The information given in this product information represents general, non-binding guidelines. No warranty expressed or implied is given concerning the properties of the product or its suitability for any given application. We therefore recommend that you consult a FUCHS LUBRICANTS GERMANY GmbH application engineer to discuss application conditions and the performance criteria of the products before the product is used. It is the responsibility of the user to test the functional suitability of the product and to use it with the corresponding care. Our products undergo continuous improvement. We therefore retain the right to change our product program, the products, and their manufacturing processes as well as all details of our product information sheets at any time and without warning, unless otherwise provided in customer-specific agreements. With the publication of this product information, all previous editions cease to be valid. Any form of reproduction requires express prior written permission from FUCHS LUBRICANTS GERMANY GmbH.

© FUCHS LUBRICANTS GERMANY GmbH. All Rights reserved. Issue 01 / 2024

**FUCHS LUBRICANTS GERMANY GmbH**

Industriestraße 35-53 ▪ 22880 Wedel/Germany ▪ Phone: 04103 9134-19 ▪ E-mail: [info-paraf fluid@fuchs.com](mailto:info-paraf fluid@fuchs.com) ▪ [www.fuchs.com/de/en](http://www.fuchs.com/de/en)