

UV Tracer

A 20% dispersion of a synthetic hydrocarbon lubricant in an isoparaffinic solvent intended as a general purpose lubricant for tin/lead connectors.

Typical Properties of the Oil		Typical Value	Test Method
Recommended Service Range (°C)		-40 to 120	
Base Oil	Type	Polyalphaolefin	
	Kinematic Viscosity	40°C	1015 cSt
		100°C	77 cSt
	Viscosity Index		158
	Flash Point	°C	40.0000
	Pour Point	°C	-29
	Density	25°C	0.85 g/cm ³
	Evaporation	24 hour(s) 150°C	1 %
			NYE CTM
Typical Properties of the Grease		Typical Value	Test Method
Color, Appearance		light yellow	
Penetration (1/10mm)	Unworked	> 300	ASTM D-217
Thickener		Silica	
Density		25°C	0.89 g/cm ³
Dropping Point		°C	> 260 (non-melting)
Oil Separation	24 hour(s)	66°C	4
			FTM 791, Method 321.2
Evaporation	24 hour(s)	150°C	1 %
			ASTM D-972
Typical Properties of the Solvent		Typical Value	Test Method
Chemical Composition		Isoparaffinic	
Concentration by Weight		80 %	
Flash Point		°C	40
Boiling Point		°C	156
Density		25°C	0.75 g/cm ³
			ASTM D-1480

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1811)