

RHEOLUBE 380-G1

Rust Inhibited, EP Fortified

A soft, lithium soap thickened, light viscosity, PAO/ester grease intended for instrument and gear applications. Excellent for wide temperature performance.

	Lubricant Properties		Typical Value	Test Method
Recommended Service Range (°C)		-50 to 130		
Thickener			Lithium Soap	
Base Oil	Туре		PAO/Ester	
	Kinematic Viscosity	100°C	6.5 cSt	ASTM D-445
		40°C	37 cSt	
		-40°C	19551 cSt	
	Viscosity Index		129.9	ASTM D-2270
	Flash Point	C°	259	ASTM D-92
	Pour Point	C°	-58	ASTM D-97
	Typical Properties of	the	Typical Value	Test Method
	Grease			
Color, Appearance			Black, Smooth	
Penetration	Worked	60X	325	ASTM D-217
(1/10 mm)	Worked	10k	349	
	Unworked		332	
	NLGI Grade		1	
Density		25°C	0.95 g/cm ³	NYE CTM
Oil Separation	24 hour(s)	100°C	18.6	ASTM D-6184
Evaporation	24 hour(s)	100°C	0.18	NYE CTM

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (2002)